

Table E	Anti-Skid Gradations								
	(based on laboratory sieve tests - square openings)								
	Total Percent Passing								
Type	37.5mm	19mm	12.5mm	9.5mm	4.75mm	2.36mm	300µm	150µm	75µm
	1-1/4 inch	3/4 inch	1/2 inch	3/8 inch	#4	#8	#50	#100	#200*
AS1				100	60 - 100	0 - 80		0 - 8	0 - 5*
AS2				100	35 - 80	0 - 45		0 - 6	0 - 3**
AS3			100	90 - 100		0 - 30		0 - 8	
AS4				100	35 - 80	0 - 45		0 - 6	0 - 3**
<i>* Determined by PTM No. 100</i>									
<i>** If total percent passing the #8 sieve is less than 25%, then the total percent passing the #200 sieve is permitted to be 0-5.</i>									
NOTES: 1. AS1 is a manufactured or natural sand (no slag permitted) 2. AS2 is a crushed stone or gravel 3. AS3 is a crushed stone or gravel specification is near #8's 4. AS4 is a SLAG ONLY material									